für / for / per / pour

K2-BONDER®

BONDER K2



YETI Dentalprodukte GmbH Industriestraße 3 D-78234 Engen / Germany www.yeti-dental.com

((() ()

Operating Instructions

1. General: K2 BONDER is suitable for Non Precious Alloys, specially for the Cobalt-Chrome

and Nickel-Chrome Alloys of the company YETI Dental.

K2 BONDER acts as a WAK buffer between Non Precious Alloys and the ceramic, and

it is easy in manipulation.

1.1. Product description/

Delivery:

Art. 337-0500

K2 Bonder Paste 5 g Tin

1.2. Technical Data: Preheating temperatur 550 °C

Drying Time 6 min.
Raise of Temperature 80 °C/min.
Vacuum Yes
Final temperature 980 °C
Holding time 1 min.

Appearance lightly shinning

1.3. Manufacturer: YETI Dentalprodukte GmbH, Industriestraße 3, D-78234 Engen, Germany

Tel.: +49-7733-94100 Fax: +49-7733-941022 e-mail-adresse: info@yeti-dental.com

Technical assistance: +49-7733-9410-20

2. Determineded use:

To be used only by dental technicians or similarly qualified people for dental restaurations in the patient's mouth.

3. Instructions for use:

- Oxidization and blasting of Frameworks must always be prepared in line with manufacturer's instruction.
- Always mix well before each use.
- Use separate brushes for applying Bonder and Opaque materials.
- Coat Bonder in a thin layer and close bottle between applications.
- The bonder will appear to be yellow in colour once fired (although yellow colour may vary slightly between different alloys).
- The paste opaque can be diluted using the "K2" glaze liquid as required. This should be done at each application and not in the product bottle.

4. Caution:

Ceramic works to be done and controlled only by dental technicians or similarly qualified people. werden.

5. Guarantee:

The user is responsible for correct use and processing. All recommendations are based on our own experience. Any claim for compensation we receive can only relate to the value of the goods which have been delivered.

6. Disposal:

Dokument:	Erstellt am/von:	geändert am/von:	Revision:	freigegeben am/von:	Seitenzahl:
ВА	30.07.2015/TB	05.10.2017/TB	0	05.10.2017/TB	Seite 1 von 1